

TECHNICAL SPECIFICATION

NOVOLIN **Type** **20PPO325, Rose**

Composition	A carded white thermobonded fibre. 100% polypropylene. Hydrophobe nonwoven impregnated with a medicinal oil.	
	U.M.	Value
Weight (impr.)	(g/sqm)	20 ± 1
Impregnation	(%)	10 – 12
Thickness (non-impr.)	(mm)	0,2
Tensile strength MD	(N/50mm)	33
Tensile strength CD	(N/50mm)	10
Elongation MD	(%)	40 max
Elongation CD	(%)	80 max
PROCESS PARAMETERS		
Speed	(m/min)	100
Pressure	(kg/cm)	70
Temperature Patterned roll	(°C)	150
Temperature Smooth roll	(°C)	145
All tests are carried out according to EDANA recommended test methods on dry nonwoven. Average values from 50 single tests min.		
Personal / environment protection : Not applicable		
Handling and storage : Normal requirements		
First-Aid measures : No specific measures to be taken		
Waddinxveen, Date : 01-01-2017		